

#### Typical chemical and physical properties

ADDAPT<sup>®</sup> Foamstop<sup>™</sup> SL 10 is a highly effective and versatile foam control agent. It is extremely stable both on storage and in the final system.

**It is a silicone emulsion containing minerals and fatty acid based emulsifiers**

Appearance	White milky liquid
Active content	10%
pH	6.0 – 7.5
Viscosity at 25 °C	300 – 1000 mPa·s
Density at 25 °C	1.00 – 1.03 g/cm <sup>3</sup>
Flash point	>160 °C
Boiling point	100 °C (Water)

*This information is intended as a guideline only. For specifications please consult the Certificate of Analyses.*

#### Applications and typical treat level recommended

Paint industry	0.05 to 0.25 % wt. based on total
Printing ink industry	0.05 to 0.25 % wt. based on total
Adhesives and glues	100 – 500 ppm based on total
Sewage and effluent treatment	100 – 500 ppm based on total
Boiler washing	100 – 500 ppm based on total
Cutting fluids	100 – 500 ppm based on total
Fertiliser manufacturing	100 – 500 ppm based on total

#### Benefits

ADDAPT<sup>®</sup> Foamstop<sup>™</sup> SL 10 shows a very rapid defoaming effect under static conditions (very rapid “killing effect”).

ADDAPT<sup>®</sup> Foamstop<sup>™</sup> SL 10 disperses easily, requiring only mild agitation.

Maintains the defoaming properties over a prolonged period of time

ADDAPT<sup>®</sup> Foamstop<sup>™</sup> SL 10 prevents the formation of macro-foam and reduces the formation of micro-foam. When used in pigmented systems; it does not influence the recoatability. It is easy emulsifiable.

2/3 of the amount should be added during the grinding stage, 1/3 during the ‘let down’ stage.

For maximum efficiency, it is recommended to dilute ADDAPT<sup>®</sup> Foamstop<sup>™</sup> SL 10 with (soft or deionised) water; ratio ADDAPT<sup>®</sup> Foamstop<sup>™</sup> SL 10 – water (1:9). The water should be added to the Foamstop<sup>™</sup> SL 10 with mild agitation.

# ADDAPT<sup>®</sup> Foamstop<sup>™</sup> SL 10

---

<b>Safety and Handling</b>	Please read Material Safety Data Sheet (MSDS) before handling.
<b>Product Specification</b>	This information is available on request through our local representative.
<b>Packaging</b>	This information is available on request through our local representative.
<b>Storage Stability</b>	At least 6 months at adequate storage

---

**Quality Policy**                      The objective of our quality policy is the continuous fulfilment of the internal and external requirements agreed upon with our partners with regards to everybody's performance.

The Quality System of ADDAPT<sup>®</sup> Chemicals BV is based on the principles of the NEN-EN-ISO-Standard 9001: 2015.

---

**Liabilities**                              *All recommendations for the use of our products, whether given by us in writing, orally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations, buyer or user remains responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility thereof. Buyer has to ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with, and subject to, our general conditions of sale and supply.*

ADDAPT Chemicals BV  
Speltdijk 1  
NL-5704 RJ Helmond  
The Netherlands  
Tel: + 31 - 492 - 59 75 75  
Fax: + 31 - 492 - 55 29 55  
E-mail: [info@addapt-chem.com](mailto:info@addapt-chem.com)  
Home page: <http://www.addapt-chem.com>

Publication Number FO82427  
© ADDAPT Chemicals BV 2022  
Version 6: 2022

